

*SAN-013* , Ortho phthalic base liquid polyester resin of a semi rigid type, low viscosity and medium reactivity with high impact resistance , especially projected for construction of FGRP products .

### **RESIN CHARACTERISTICS ( BEFORE POLYMERISATION )**

PROPERTY	STANDARD
State	Liquid
Monomer content %	34 - 36
Viscosity @ 25 °C ( Brookfield viscometer )	260 – 340 centi poises
Aspect	Clear Amber
Hazen colouring	<150
Specific gravity @ 20 °C	1.12 ± 0.07
Refractive index @ 25 °C	1.54 ± 0.007
Acid index ( mg KOH / g resin )	25 ± 3
Conservation @ 25 °C in closed package min.	6 months

### **POLYMERIZATION CHARACTERISTICS**

The polymerization can also be effected in cold, in this case, the addition of an accelerator is necessary. The following indicates the gel time obtained in standard work conditions, which can serve as an approximate indication.

Accelerator	Catalyst	Temperature	Gel time ( min. )	Peak temp.
C3 1%	M8 2%	25 °C	10-15	150-170 °C

C3 =COBALT OCTOATE OF 1.5 % Co

M8 = MEK PEROXIDE OF 50%

*Please note that the gel time is the standard that we produce however, we can modify to suite your requirment*

**N.B** *since operatinge conditions in the user's plant are beyond our control . we cannot assume liabilities which may result from the use of our product.*

*Rev.02*